

Advancements and Challenges in 3D Printing of Electroconductive Hydrogels for Cardiovascular Bioprinting

ARTICLE INFO

Article Type Narrative Review

Authors

Fatemeh Edrisi1

Nafiseh Baheiraei*2

Modern technologies in Engineering 1-Group, Faculty of Interdisciplinary Science and Technology, Tarbiat Modares University, Tehran, Iran. 2- Tissue Engineering and Applied Cell Department Sciences Division, of Anatomical Sciences, Faculty of Medical Sciences, Tarbiat Modares University, Tehran, Iran.

*Corresponding author:

Nafiseh Baheiraei

Tissue Engineering and Applied Cell Sciences Division, Department of Anatomical Sciences, Faculty of Medical Sciences, Tarbiat Modares University, Tehran.

1411713116, Iran.

E-mail: n.baheiraei@modares.ac.ir.

ABSTRACT

Cardiovascular diseases (CVDs) are the most prevalent cause of fatalities worldwide, affecting both cardiac and vascular tissues. Tissue engineering is a promising treatment alternative for people with end-stage CVDs; however, it has disadvantages such as poor scaffold design control and insufficient vascularization. 3D bioprinting, a recent advancement, has overcome these restrictions by creating layer-by-layer structures such as organs, scaffolds, and blood vessels. This method enables precise control over cell distribution, architectural structure, and compositional correction. Furthermore, since cardiac tissue is electroactive, incorporating electroconductive nanomaterials into the scaffold facilitates intracellular communication, mimics the heart's biochemical and biomechanical microenvironment, and prevents arrhythmia in the heart. In addition, these electroconductive materials can improve the quality of 3D-printed scaffolds. In this study, we will review the different techniques of 3D printing hydrogels after evaluating the many types of hydrogels employed for cardiac tissue engineering (CTE). Then, we will discuss the influence of incorporating electroconductive fillers into hydrogels on printed scaffold quality. Finally, we will briefly discuss the challenges and potentials.

Keywords: 3D bioprinting, Cardiac tissue engineering, Electroconductive hydrogels

Copyright© 2020, TMU Press. This open-access article is published under the terms of the Creative Commons Attribution-NonCommercial 4.0 International License which permits Share (copy and redistribute the material in any medium or format) and Adapt (remix, transform, and build upon the material) under the Attribution-NonCommercial terms

INTRODUCTION

Cardiovascular diseases (CVDs) were the primary cause of mortality for 19.9 million people worldwide in 2021, which included 37% of deaths under the age of 70 globally [1]. CVDs are chronic pathological conditions affecting cardiac and vessel tissues, such as coronary heart disease, rheumatic heart disease, and cerebrovascular disease. Myocardial infarction (MI) is the leading cause of CVDs, occurring when plaques in the coronary arteries rupture or erode, producing blood clots and restricting circulation in the heart, completely or partially. This results in hypoxiainduced cardiomyocyte (CM) death and severe inflammation, leading cardiac tissue to degeneration and the creation of scar tissue in the infarcted area [2-5]. Cardiac transplantation is the gold standard therapeutic procedure for patients with end-stage heart failure. While it has achieved clinical success, there are still many challenges and drawbacks to this method, such as the lack of donors, the possibility of organ rejection by the immune system, and the need for immunosuppressive drugs [6]. As a result, innovative treatment procedures such as cell transplantation have been assessed as promising novel treatments for cardiac tissue regeneration for more than two decades. However, cell engraftment and the viability of transplanted stem

cells in the host body are major constraints of stem cell treatment. Furthermore, stem cells cannot develop into more adult-like phenotypes and are unable to generate extracellular matrix (ECM) and vascularization after injection, resulting in sluggish conduction and spontaneous activity, which can lead to fatal arrhythmias after transplantation [7-9]. Tissue engineering is a promising treatment strategy for end-stage CVDs; it can reduce complications and overcome the limitations of cell-based therapeutics. An optimal scaffold for cardiac tissue engineering (CTE) should be morphologically, electromechanically, and biologically similar to the original ECM [10]. Construction procedures for this 3D architecture range from the simple use of hydrogels to electrospun nanofibers and decellularized tissues. However, poor scaffold architecture control, incomplete vascularization, and a lack of cell types that can aid in damaged tissue reconstruction have restricted their efficacy [11]. The 3D bioprinting method is one of the recent promising procedures that has allowed us to overcome these restrictions. Using various components such as biomaterials, living cells, growth factors, and bioactive substances, this approach produces structures layer-by-layer in the form of various organs, scaffolds, and blood vessels. These structures can partially or completely replace natural organs in the targeted host location [12-16]. Bioprinting allows for precise control over the geographical distribution of cells, architectural structure, and compositional correction. Furthermore, it can provide a highly continuous and stable biological structure, allowing for a high-resolution simulation of the heart and paving the path for innovative research into cardiac tissue repair and regeneration using novel technology. Nevertheless, 3D bioprintingbased heart regeneration technology is still in its phases of development, requiring early collaboration among experts to study bioink characteristics at physical and chemical levels to better define myocardial architecture and physiological diversity [17].

Because the heart is an electroactive tissue that can transmit electrical signals, an electromechanical connection between CMs is required for synchronous response to these electrical signals and regulation of cardiac cell processes (such as adhesion, proliferation, and migration) [18, 19]. Nowadays, a number of electroconductive biomaterials are used in the field of CTE. The materials include carbon-based nanomaterials [20], gold-based nanomaterials [21], conductive polymers [22], piezoelectric polymeric materials [23], melanin [24], silicon nanowires [25], silver nanoparticles [26], and selenium nanoparticles [27]. Some studies have previously reviewed the potential applications of 3D printing technology in CTE, focusing on the type of bioink and the type of cells [28-30]. In this study, we will reference the types of hydrogels utilized in CTE and subsequently review the various methods of 3D printing hydrogels. The influence of incorporating electroconductive elements into the hydrogels on the printed scaffolds and the print quality will also be discussed in this review.

Hydrogels as a bioink

Hydrogels are 3D structures of cross-linked hydrophilic polymers that have excellent water absorption capabilities. Hydrogel-based 3D bioprinting has the benefit of developing living structures from bio-inks that contain live cells, growth factors, and other biocompatible components [31]. Bio-inks are categorized into both naturally derived and synthetic materials. Naturally produced materials are more widely employed because of their inherent biocompatibility and near resemblance to the ECM. Natural polymer hydrogels mostly involve polysaccharide-based (agarose, alginate. chitosan), protein-based (collagen, gelatin, fibrin, Matrigel), glycosaminoglycan-based (hyaluronic acid, heparin), or even decellularized ECM [16, 32-37]. It is noteworthy that among naturally derived hydrogels, alginate and collagen are the most commonly used in bioprinting, followed by gelatin methacrylate (GelMA), fibrinogen, and gelatin [38]. The recognition of this group as the most common application component of bioinks stems from their high biological activity and their natural presence in the human body, such as collagen. However, their shortcomings for 3D bioprinting include insufficient mechanical strength, poor rheological characteristics, the tendency to generate immunological responses, and batch-to-batch variability [39]. On the other hand, synthetic hydrogel polymers generally of polyacrylic acid derivatives, consist polyethylene glycol copolymers, polyvinyl alcohol, polyphosphazene, and synthetic peptides [40, 41]. The biocompatibility of synthetic hydrogels is inferior to that of naturally extracted but their powerful mechanical hydrogels, simplicity of control, and low properties, immunogenicity are their advantages, which attract much attention in fields of tissue engineering such as cardiovascular regeneration [42, 43].

3D bioprinting techniques

The literature describes a variety of techniques for fabricating 3D scaffolds, including solvent casting, molding, electrospinning, and 3D printing [44]. In recent years, 3D printing of hydrogels has received increasing research interest as a reasonable manufacturing strategy for biomedical applications, especially in tissue engineering. Innovative technology for 3D printing of living cells and biomaterials to produce complex scaffolds in CTE comprises droplet-inkjet [45], extrusion-based [46], and laser-assisted bioprinting [47], which will be explained in the next section.

Extrusion-based printing

Extrusion-based bioprinting is a common approach for constructing cardiovascular tissues by distributing cells across a hydrogel matrix altogether and depositing them layer-by-layer, as well as the deposition of a melted polymeric filament known as fused deposition modeling (FDM) [29]. In this method, the pneumatic or mechanical (piston or screw-based) dispensing mechanism extrudes bioinks through nozzles and deposits them on the printed platform [29]. A wide range of choices of materials, ranging from pristine polymers to composite materials, have been used in this procedure [48, 49]. Interestingly, this is the only printing process that has been effectively utilized for 3D bioprinting of electroconductive hydrogels [50]. As the bio-ink should have a low elastic shear modulus under high shear stress to move through the nozzle and a high static elastic modulus to preserve its form after deposition for printing several layers, the rheological properties of the bioinks, such as

shear-thinning features and viscosity, play a vital role in the extrusion-based printing method [51]. Nevertheless, the death of cells due to the induced shear stress during the printing technique and also the poor print resolution are the main shortcomings of this technique [52].

Droplet-inkjet printing

Inkjet bioprinting is a popular 3D printing technology for biological purposes. The process involves delivering a regulated volume of bioinks, often including cells, to preset areas via a thermal or piezoelectric mechanism [53]. This approach promotes exact control of implanted cells, growth factors, genes, and medications and is compatible with a wide range of biomaterials. The great resolution of the droplet-inkjet structure, due to the creation of small droplets, is the key benefit of this technique that allows for precise geometry and scaffold size management. Furthermore, because of its high-speed printing this technology and cost-effectiveness, is frequently employed in the field of blood vessels 55]. However, inkjet bioprinting needs [54. bioinks with low viscosity (3.5-20 mPa·s), resulting in produced constructions with poor structural integrity and mechanical strength. Other drawbacks of this method involve irregular droplet directionality, droplet size, low mechanical and shear stresses on the cells, and repeated nozzle blockage. In addition, controlling the number of cells to be enclosed in a single droplet is another issue that would be considered [52, 56].

Laser-assisted printing

In contrast to extrusion and inkjet bioprinting, where bioinks rely primarily on continuous external mechanical force and gravity to construct a 3D structure, laser-assisted bioprinting relies on precise optical guidance [17]. A pulsed laser beam, a ribbon containing bioink, and a receptive substrate create a laser-assisted bioprinter system. The laser interacts with the ribbon, ejecting droplets of bioink, usually containing cells, onto the substrate. Laser-assisted printing is a nozzlefree technique that eliminates nozzle clogging and maximizes cell viability by reducing mechanical stress during the printing process. The deposition of high cell densities and excellent resolution are among its advantages. In addition, this method can employ a wide range of biomaterials with varying viscosities (1–300 mPa·s). Despite these benefits, it is mostly utilized for 2D bioprinting (monolayer) and is often ineffective for depositing multiple cell types. Because it is time-consuming, expensive, and works with small-sized constructs, its clinical applications are limited [56].

Stereolithography (SLA) is another 3D printing method based on a laser. SLA is the technique of converting a photocurable polymer solution into a photopolymerized solid in a layerby-layer form with light energy, such as a UV or laser beam. This procedure solidifies a liquid resin, producing the desired pattern in a resin bath. SLA is employed for high-resolution electroconductive hydrogel printing and is compatible with a wide range of materials [57-60]. The primary advantage of this approach is the shape fidelity of hydrogels after printing. Because of its contactless method, SLA has great cell viability and also allows for the construction of complex patterns with high resolution, such as vascular networks with various scales (50-250 μm) [54, 59, 61]. However, SLA has limitations due to the need for photosensitive materials, which can restrict bioink selection. In addition, the requirement of incorporating a cell type into a hydrogel limits other possible bioinks. Moreover, laser diodes are typically more expensive than nozzles, and there is the possibility of cell side effects after laser exposure during manufacturing [54, 59, 62]. Considering the variety of 3D printing methods and the fact that the ideal bioinks for each method require prerequisites, selecting the appropriate 3D printing approach might vary depending on the type of hydrogel and the intended application.

Influence of incorporating electroconductive biomaterials in the printability of hydrogels

As previously stated, electroconductivity is critical for biomaterials in CTE because the heart has a conduction system and beats spontaneously at a rhythm. Additionally, CMs require a conductive microenvironment for electromechanical coupling. Despite nonconductive materials being used in research and clinical trials, efforts are ongoing to find effective electroconductive biomaterials for improving CTE [63]. On the other hand, blockage of conduction non-conductive scaffolds by implanted in the desired location, similar to the fibrotic tissue formed after MI, leads to asynchronous contractions of some parts of the heart, which may lead to progressive heart failure [19]. Therefore, the regeneration of a similar biostructure as the ultimate objective of 3D bioprinting needs to be performed in a manner that can retain and establish the requisite biophysical stimulations, including electrical. A varied range of electroconductive biomaterials carbon-based, gold-based, conductive like polymers, piezoelectric polymeric materials, melanin, silicon nanowires, silver nanoparticles, and selenium nanoparticles are widely used in CTE [64]. Also, MXenes and liquid metals have recently attracted increased study attention in the field of biomedical engineering because of their desirable collection of features, including hydrophilicity high fluidity, metallic or conductivity, and strong biocompatibility [65, group published 66]. Recently, our comprehensive that overview thoroughly examined the advantages and challenges associated with graphene-based nanomaterials in the field of CTE [63]. Such conductive filler materials not only provide the capacity to tune the physicochemical desired structure and characteristics of printed hydrogels, but they also alter the rheological properties of inks during 3D scaffold creation, and these additives can affect the ultimate quality of the printed scaffold [67-69]. Designing a bioink involves evaluating important factors such as printability, stability, biology, rheology, viscosity, gelation. and crosslinking ensure capacities to optimal performance. In addition, the design deviation is determined by bioink parameters like viscosity, shear stress, and fidelity. While increasing viscosity enhances shape fidelity, the increased shear stress may damage cells and produce deceptive biophysical signals. The fidelity of a 3D-constructed structure is dependent on the rapid transition to a solid state following deposition, and also decreasing gelification time enhances structural resolution [58, 70]. As a result, selecting the proper electroactive fillers for bioinks is critical as it affects the main

characteristics, including rheological and mechanical features. Table 1 presented some applying studies about recent the electroconductive hydrogels in 3D printing for CTE. In a study, Moya and his colleagues assessed the influence of combining alginatebased hydrogels with graphene oxide (GO) for 3D printing of scaffolds. The obtained results indicate that with the addition of GO, a significant reduction in recovery time was established. This could be because the GO sheets can interact with the polymer chains through hydrogen bonding, and the GO acts as a physical binder, thus it can improve the viscosity recovery time [71]. Additionally, a study has been conducted in the field of heart tissue repair, during which carbon nanotubes and a scaffold constructed of alginate, methacrylate collagen, and human coronary artery endothelial cells were synthesized using 3D printing method. The obtained results indicated that the existing cells had proper proliferation, migration and differentiation and created patches with vascularization potential before implantation in the body environment. The electromechanical properties of these scaffolds were also suitable [69]. A composite of alginate and GO was fabricated for bone tissue engineering by extrusion-based 3D printing. It was shown that the addition of GO to alginate hydrogel significantly enhanced the printing performance of the prepared bioink. 3D printed scaffolds showed significant improvement compared to those printed with mesenchymal stem cells and alginate. Furthermore, shear thinning behavior in hydrogels containing GO was observed. Among the other findings were a decrease in the pressure required for printing as well as a decrease in the thickness of the printed strands after adding GO, which can be very useful for cell-laden printing because it reduces the shear stress applied to the cells and can improve the exchange of nutrients and oxygen to the encapsulated cells. The resulting composites are suitable in terms of printing ability, structural stability, induction of bone formation, and use in the repair of other tissues [68]. In another study, Serafin et al. created a scaffold from the composition of gelatin-hyaluronic acid containing polypyrrole as a conductive polymer. They 3D printed their scaffolds with an extrusion-based printer. They

discovered that the printed scaffolds had high shape fidelity. They stated that adding polypyrrole nanoparticles to hydrogels effectively acted as a filler and that all bioinks had solid-like behavior. Furthermore, the viscosity of bioinks rose with the addition of different quantities of polymer additives, and the homogenous viscosity recovery profile for those with additives happened 5-10 seconds after eliminating the shear stress. Also, the electrical conductivity of the scaffold increased with the addition of polypyrrole. experiments In vitro also demonstrated that the samples containing the additive had 87% viability. They suggested that the created scaffold might be used for electroactive tissue engineering applications such as nerve tissue, cardiac tissue, and spinal cord [72]. In a study, a cardiac patch was developed using aerosol jet printing technology, in which conductive titanium carbide (Ti3C2Tx) MXene nanoparticles were printed in the form of an aerosol on a PEG substrate with regular patterns. And then were seeded induced pluripotent stem cell derived CMs on the Ti3C2Tx MXene-PEG composite in a regular pattern. They claimed that their research was a breakthrough in 3D printing with cellular-level resolution. This fabricated structure has no signs of cytotoxicity 7 days after cell culturing. Furthermore, it demonstrated that the gene expression of MYH7, SERCA2, and TNNT2 increased significantly. And also the synchronous beating as well as electroconductivity improved [73].

Methacrylated collagen (MeCol). Carbon nanotubes (CNTs). Human coronary artery endothelial cells (HCAECs). Chondroitin sulfate Human adipose (CS). tissue derived A mesenchymal stem cells (hADMSCs). Polyethylene diacrylate glycol (PEGDA). Polyaniline (PANI). Mouse cardiac progenitor cells (mCPCs). Titanium carbide (Ti3C2Tx). Human induced pluripotent stem cell derived cardiomyocytes (iCMs). Methacrylated Hyaluronic Acid (MeHA). Human umbilical vein endothelial cells (HUVECs). Human induced pluripotent stem cell derived cardiomyocytes (hiPSC-derived CMs).Polypyrrole (PPy). Mesenchymal stem cells (MSCs). Neuronal stem cells (NSCs). Poly(vinyl alcohol) (PVA). Gallic acid (GA).

Biomaterials	Electroconduct ive nanomaterials	3D printing technique	Cell type	In vitro/in vivo	Main results	Ref
MeCol/ Alginate	CNTs	UV-assisted 3D bioprinting	HCAECs	+/-	 ↑ Stiffness ↑ Storage modulus ↑ Electrical conductivity ↑ Proliferation, migration, and differentiation of cells 	[69]
(Alginate/ CS/ Gelatin) methacrylat e	GO	Micro-extrusion 3D bioprinting	hADMSCs	+/-	 ↑Shape fidelity ↑ Recovery of viscosity after printing ↑ Resolution of 3D printed structures ↑ Cell viability and directed proliferation ↑ Printability ↑ Mechanical strength 	[71]
PEGDA	PANI	Micro- stereolithograph y	mCPCs	+/-	Mimicking the bio-structure of myocardium Rough geometry and irregular pore size due to the ineffective photo-polymerization reaction in hydrogel solution depending on PANI concentration ↑ Strand diameter and pore size ↑ Electrical conductivity ↑ Cell viability	[74]
PEG	Ti3C2T <i>x</i> - MXene	Aerosol jet printing	iCMs	+/-	Possibility of cell-level resolution in printing ↑ Expression of MYH7, SERCA2, and TNNT2 ↑ Cell alignment and viability ↑ The synchronous beating of cells	[73]
MeHA	Thiophene	Stereolithograp hy 3D printing	HUVECs and hiPSC-derived CMs	+/-	 ↑ Viscosity of bioink ↑ Storage modulus ↓ Loss modulus after 3D printing process Solid and stable printed scaffold ↑ Beat rate of cells Biocompatible scaffold 	[47]
Gelatin/HA	РРу	Extrusion 3D bioprinting	MSCs and NSCs	+/-	Shear-thinning behaviour of hydrogel Solid-like behaviour of hydrogel ↑ Storage and loss modulus ↑ Viscosity of bioink ↑ Shape fidelity Homogenous viscosity recovery profile High cell viability and attachment	[72]
Fibrinogen	GO	Extrusion 3D bioprinting	MSCs	+/+	Mechanical and regeneration support for the infarcted area ↑ Expression of connexin 43 ↓ Cell apoptosis after MI ↑ Cardiac function	[75]
PVA/ GA	PEDOT	Extrusion 3D bioprinting	Mouse CMs	+/+	Solid-like behaviour of hydrogel ↑ storage and loss modulus ↑ Elasticity Be able to propagating the electrical signal ↑ Cardiac function	[76]
PGS/ TOCNF	РРу	Extrusion 3D bioprinting	H9c2	+/-	↑ Young's modulus and Elongation Shear-thinning behaviour of hydrogel Approved cell biocompatibility, proliferation and attachment	[77]
Alginate/ Gelatin	CNFs	Extrusion 3D bioprinting	NIH/3T3 fibroblasts	+/-	 ↑ Young's modulus Shear-thinning behaviour of hydrogel Solid-like behaviour of hydrogel ↑ Viscosity of bioink Recovery of viscosity for all hydrogel after printing Approved cell biocompatibility 	[78]

Table 1. Some recent studies about applying the lectroconductive hydrogels in 3D printing for CTE.

Poly(3,4 ethylenedioxythiophene) (PEDOT).Poly(glycerol sebacate)(PGS).2,2,6,6-tetramethylpiperidine-1-oxyl radical-oxidizednanocellulose (TOCNF).carbon nanofibers(CNFs).NIH3T3 mouseembryonic fibroblast cells (NIH/3T3 fibroblasts)

CONCLUSION AND PROSPECTS OF FUTURE

3D printing of electroconductive hydrogels is a key research area in bioelectronics, implants, and medical devices, particularly in cardiovascular bioprinting. The 3D printing technique has the potential to produce structures on a very small scale, such as vascular networks, as well as print cardiac patches and even complete organs; however, the latter has a very long way to go to achieve clinical applications. Bioinks are created by combining various cell types, hydrogels, and biochemical factors to mimic the structure and function of heart tissue. Despite the outstanding advancement in 3D printing in recent years, 3D bioprinting-based heart regeneration technology is still in its early stages of advancement, requiring collaboration among experts to study bioink characteristics at the physical and chemical levels to better define myocardial architecture and physiological diversity. The investigation of emerging technologies such as 4D printing in the field of 3D printing of electroconductive hydrogels still needs to be studied. However, some studies have been conducted on the development of 4D printing by using materials sensitive to infrared light and temperature, pHresponsive, and electric field-responsive, which require more serious efforts to reach clinical step [67, 79-81]. Also, the combination of other fabrication methods, such as electrospinning and 3D printing, can pave the way for more precise control of the geometry of printed structures for tissue engineering. There are four ways to approach this combination: 1- 3D printing of the scaffold on the electrospun membrane; 2- 3D printed scaffold covered with electrospun fibers; 3- Infusion or crosslinking electrospun fibers into the printed structure; and 4- Layer-by-layer placement of the electrospun membrane and 3D printed grid [67]. To sum up, 3D printing technology is an emerging technology with many potentials in various fields such as medicine, industry, electronics, etc., which has attracted the attention of tissue engineering researchers, especially cardiac tissue engineering, due to its many advantages. Nevertheless, it can be said that it is still in the early stages of its development and requires more serious research. Furthermore, finding a bioink with suitable biological, rheological, and mechanical properties that is printable and suitable for cardiac tissue engineering applications is still a challenge that requires more studies in this field.

CONFLICTS OF INTEREST

There are no conflicts to declare.

REFERENCES

- [1] 1. Martin SS, Aday AW, Almarzooq ZI, Anderson CAM, Arora P, Avery CL, et al. 2024 Heart Disease and Stroke Statistics: A Report of US and Global Data From the American Heart Association. Circulation. 2024;149(8):e347-e913.
- [2] 2. White HD, Chew DP. Acute myocardial infarction. Lancet. 2008;372(9638):570-84.
- [3] 3. Mandla S, Radisic M. Cardiac tissue. Principles of Regenerative Medicine: Elsevier; 2019. p. 1073-99.
- [4] 4. Jang J. 3D bioprinting and in vitro cardiovascular tissue modeling. Bioengineering. 2017;4(3):71.
- [5] 5. Cui H, Miao S, Esworthy T, Zhou X, Lee S-j, Liu C, et al. 3D bioprinting for cardiovascular regeneration and pharmacology. Adv Drug Deliv Rev. 2018;132:252-69.
- [6] 6. Tallawi M, Rosellini E, Barbani N, Cascone MG, Rai R, Saint-Pierre G, et al. Strategies for the chemical and biological functionalization of scaffolds for cardiac tissue engineering: a review. Journal of the Royal Society Interface. 2015;12(108):20150254.
- [7] 7. Valls Margarit M. Development of an advanced 3D culture system for human cardiac tissue engineering. [PHD's thesis]. Barcelona: Barcelona University; 2017.
- [8] 8. Chong JJ, Yang X, Don CW, Minami E, Liu Y-W, Weyers JJ, et al. Human embryonic-stemcell-derived cardiomyocytes regenerate nonhuman primate hearts. Nature. 2014;510(7504):273-7.

- [9] 9. Behfar A, Crespo-Diaz R, Terzic A, Gersh BJ. Cell therapy for cardiac repair—lessons from clinical trials. Nat Rev Cardiol. 2014;11(4):232-46.
- [10] 10. Qasim M, Haq F, Kang M-H, Kim J-H. 3D printing approaches for cardiac tissue engineering and role of immune modulation in tissue regeneration. Int J Nanomedicine. 2019:1311-33.
- [11] 11. Subia B, Kundu J, Kundu S. Biomaterial scaffold fabrication techniques for potential tissue engineering applications. Tissue Eng. 2010;141(13-18).
- [12] 12. Murphy SV, Atala A. 3D bioprinting of tissues and organs. Nat Biotechnol. 2014;32(8):773-85.
- [13] 13. Do A-V, Khorsand B, Geary SM, Salem AK. 3D Printing of Scaffolds for Tissue Regeneration Applications. Adv Healthc Mater. 2015;4(12):1742-62.
- [14] 14. Liu W, Zhang YS, Heinrich MA, De Ferrari F, Jang HL, Bakht SM, et al. Rapid Continuous Multimaterial Extrusion Bioprinting. Adv Mater. 2017;29(3):1604630.
- [15] 15. Skylar-Scott MA, Uzel SGM, Nam LL, Ahrens JH, Truby RL, Damaraju S, et al. Biomanufacturing of organ-specific tissues with high cellular density and embedded vascular channels. Science Advances. 2019;5(9):eaaw2459.
- [16] 16. Noor N, Shapira A, Edri R, Gal I, Wertheim L, Dvir T. 3D Printing of Personalized Thick and Perfusable Cardiac Patches and Hearts. Advanced Science. 2019;6(11):1900344.
- [17] 17. Liu N, Ye X, Yao B, Zhao M, Wu P, Liu G, et al. Advances in 3D bioprinting technology for cardiac tissue engineering and regeneration. Bioact Mater. 2021;6(5):1388-401.
- [18] 18. Baheiraei N, Yeganeh H, Ai J, Gharibi R, Azami M, Faghihi F. Synthesis, characterization and antioxidant activity of a novel electroactive and biodegradable polyurethane for cardiac tissue engineering application. Mater Sci Eng, C. 2014;44:24-37.
- [19] 19. He S, Song H, Wu J, Li S-H, Weisel RD, Sung H-W, et al. Preservation of conductive propagation after surgical repair of cardiac defects with a bio-engineered conductive patch. The Journal of Heart and Lung Transplantation. 2018;37(7):912-24.

- [20] 20. Baheiraei N, Razavi M, Ghahremanzadeh R. Reduced graphene oxide coated alginate scaffolds: potential for cardiac patch application. Biomaterials Research. 2023;27(1):109.
- [21] 21. Malki M, Fleischer S, Shapira A, Dvir T. Gold Nanorod-Based Engineered Cardiac Patch for Suture-Free Engraftment by Near IR. Nano Lett. 2018;18(7):4069-73.
- [22] 22. Roshanbinfar K, Vogt L, Greber B, Diecke S, Boccaccini AR, Scheibel T, et al. Electroconductive Biohybrid Hydrogel for Enhanced Maturation and Beating Properties of Engineered Cardiac Tissues. Adv Funct Mater. 2018;28(42):1803951.
- [23] 23. Doustvandi B, Imani R, Yousefzadeh M. Study of Electrospun PVDF/GO Nanofibers as a Conductive Piezoelectric Heart Patch for Potential Support of Myocardial Regeneration. Macromol Mater Eng. 2024;309(1):2300243.
- [24] 24. Kai D, Prabhakaran MP, Jin G, Ramakrishna S. Biocompatibility evaluation of electrically conductive nanofibrous scaffolds for cardiac tissue engineering. J Mater Chem B. 2013;1(17):2305-14.
- [25] 25. Schmidt V, Wittemann JV, Senz S, Gösele U. Silicon nanowires: a review on aspects of their growth and their electrical properties. Adv Mater. 2009;21(25-26):2681-702.
- Nazari H, Azadi S, Hatamie S, [26] 26. Zomorrod MS, Ashtari K, Soleimani M, et al. Fabrication of graphene-silver/polyurethane cardiac nanofibrous scaffolds for tissue engineering. Polym Adv Technol. 2019;30(8):2086-99.
- [27] 27. Kalishwaralal K, Jeyabharathi S, Sundar K, Selvamani S, Prasanna M, Muthukumaran A. A novel biocompatible chitosan–Selenium nanoparticles (SeNPs) film with electrical conductivity for cardiac tissue engineering application. Mater Sci Eng, C. 2018;92:151-60.
- [28] 28. Lu TY, Xiang Y, Tang M, Chen S. 3D Printing Approaches to Engineer Cardiac Tissue. Curr Cardiol Rep. 2023;25(6):505-14.
- [29] 29. Kalhori D, Zakeri N, Zafar-Jafarzadeh M, Moroni L, Solati-Hashjin M. Cardiovascular 3D bioprinting: A review on cardiac tissue development. Bioprinting. 2022;28:e00221.

- [30] 30. Wang Z, Wang L, Li T, Liu S, Guo B, Huang W, et al. 3D bioprinting in cardiac tissue engineering. Theranostics. 2021;11(16):7948-69.
- [31] 31. Unagolla JM, Jayasuriya AC. Hydrogel-based 3D bioprinting: A comprehensive review on cell-laden hydrogels, bioink formulations, and future perspectives. Applied Materials Today. 2020;18:100479.
- [32] 32. Bejleri D, Davis ME. Decellularized Extracellular Matrix Materials for Cardiac Repair and Regeneration. Adv Healthc Mater. 2019;8(5):e1801217.
- [33] 33. Wang Z, Lee SJ, Cheng H-J, Yoo JJ, Atala A. 3D bioprinted functional and contractile cardiac tissue constructs. Acta Biomater. 2018;70:48-56.
- [34] 34. Khoshnood N, Zamanian A. Development of novel alginate-polyethyleneimine cell-laden bioink designed for 3D bioprinting of cutaneous wound healing scaffolds. J Appl Polym Sci. 2022;139(21):52227.
- [35] 35. Lee A, Hudson AR, Shiwarski DJ, Tashman JW, Hinton TJ, Yerneni S, et al. 3D bioprinting of collagen to rebuild components of the human heart. Science. 2019;365(6452):482-7.
- [36] 36. Alave Reyes-Furrer A, De Andrade S, Bachmann D, Jeker H, Steinmann M, Accart N, et al. Matrigel 3D bioprinting of contractile human skeletal muscle models recapitulating exercise and pharmacological responses. Communications biology. 2021;4(1):1183.
- [37] 37. Noh I, Kim N, Tran HN, Lee J, Lee C. 3D printable hyaluronic acid-based hydrogel for its potential application as a bioink in tissue engineering. Biomaterials research. 2019;23(1):3.
- [38] 38. Stapenhorst França F, Garrido dos Santos M, Prestes J, Alcantara B, Borges M, Pranke P. Bioprinting: A promising approach for tissue regeneration. Bioprinting. 2021;22:e00130.
- [39] 39. Liu N, Ye X, Yao B, Zhao M, Wu P, Liu G, et al. Advances in 3D bioprinting technology for cardiac tissue engineering and regeneration. Bioactive Materials. 2021;6(5):1388-401.
- [40] 40. Morgan FL, Moroni L, Baker MB. Dynamic bioinks to advance bioprinting. Adv Healthc Mater. 2020;9(15):1901798.
- [41] 41. Konta AA, García-Piña M, Serrano DR. Personalised 3D printed medicines: which

techniques and polymers are more successful? Bioengineering. 2017;4(4):79.

- [42] 42. Ji S, Almeida E, Guvendiren M. 3D bioprinting of complex channels within cell-laden hydrogels. Acta Biomater. 2019;95:214-24.
- [43] 43. Datta LP, Manchineella S, Govindaraju T. Biomolecules-derived biomaterials. Biomaterials. 2020;230:119633.
- [44] 44. Zhao P, Gu H, Mi H, Rao C, Fu J, Turng L-s. Fabrication of scaffolds in tissue engineering: A review. Frontiers of Mechanical Engineering. 2018;13(1):107-19.
- [45] 45. Christensen K, Xu C, Chai W, Zhang Z, Fu J, Huang Y. Freeform inkjet printing of cellular structures with bifurcations. Biotechnology and Bioengineering. 2015;112(5):1047-55.
- [46] 46. Bejleri D, Streeter BW, Nachlas ALY, Brown ME, Gaetani R, Christman KL, et al. A Bioprinted Cardiac Patch Composed of Cardiac-Specific Extracellular Matrix and Progenitor Cells for Heart Repair. Adv Healthc Mater. 2018;7(23):1800672.
- [47] 47. Stark BL. Development of a 3D printed conductive biopolymer for cardiac tissue engineering: The University of Texas at El Paso; 2023.
- [48] 48. Yuk H, Lu B, Lin S, Qu K, Xu J, Luo J, et al. 3D printing of conducting polymers. Nature Communications. 2020;11(1):1604.
- [49] 49. Jakus AE, Secor EB, Rutz AL, Jordan SW, Hersam MC, Shah RN. Three-Dimensional Printing of High-Content Graphene Scaffolds for Electronic and Biomedical Applications. ACS Nano. 2015;9(4):4636-48.
- [50] 50. Spencer AR, Shirzaei Sani E, Soucy JR, Corbet CC, Primbetova A, Koppes RA, et al. Bioprinting of a Cell-Laden Conductive Hydrogel Composite. ACS Appl Mater Interfaces. 2019;11(34):30518-33.
- [51] 51. Tran TS, Dutta NK, Choudhury NR. Poly(ionic liquid)-Stabilized Graphene Nanoinks for Scalable 3D Printing of Graphene Aerogels. ACS Applied Nano Materials. 2020;3(11):11608-19.
- [52] 52. Kačarević ŽP, Rider PM, Alkildani S, Retnasingh S, Smeets R, Jung O, et al. An introduction to 3D bioprinting: possibilities,

challenges and future aspects. Materials. 2018;11(11):2199.

- [53] 53. Cui X, Boland T, D.D, apos, Lima D, Martin KL. Thermal Inkjet Printing in Tissue Engineering and Regenerative Medicine. Recent Patents on Drug Delivery & Formulation. 2012;6(2):149-55.
- [54] 54. Zhang B, Gao L, Ma L, Luo Y, Yang H, Cui Z. 3D bioprinting: a novel avenue for manufacturing tissues and organs. Engineering. 2019;5(4):777-94.
- [55] 55. Hewes S, Wong AD, Searson PC. Bioprinting microvessels using an inkjet printer. Bioprinting. 2017;7:14-8.
- [56] 56. Agarwal T, Fortunato GM, Hann SY, Ayan B, Vajanthri KY, Presutti D, et al. Recent advances in bioprinting technologies for engineering cardiac tissue. Mater Sci Eng, C. 2021;124:112057.
- [57] 57. Wu Y, Chen YX, Yan J, Quinn D, Dong P, Sawyer SW, et al. Fabrication of conductive gelatin methacrylate–polyaniline hydrogels. Acta Biomater. 2016;33:122-30.
- [58] 58. van Kampen K, Scheuring R, Terpstra M, Levato R, Groll J, Malda J, et al. Biofabrication: From Additive Manufacturing to Bioprinting. 2019.
- [59] 59. Mandrycky C, Wang Z, Kim K, Kim D-H. 3D bioprinting for engineering complex tissues. Biotechnol Adv. 2016;34(4):422-34.
- [60] 60. Guvendiren M, Molde J, Soares
 RMD, Kohn J. Designing Biomaterials for 3D
 Printing. ACS Biomater Sci Eng. 2016;2(10):1679-93.
- [61] 61. Zhu W, Qu X, Zhu J, Ma X, Patel S, Liu J, et al. Direct 3D bioprinting of prevascularized tissue constructs with complex microarchitecture. Biomaterials. 2017;124:106-15.
- [62] 62. Moroni L, Boland T, Burdick JA, De Maria C, Derby B, Forgacs G, et al. Biofabrication: A Guide to Technology and Terminology. Trends Biotechnol. 2018;36(4):384-402.
- [63] 63. Edrisi F, Baheiraei N, Razavi M, Roshanbinfar K, Imani R, Jalilinejad N. Potential of graphene-based nanomaterials for cardiac tissue engineering. J Mater Chem B. 2023.
- [64] 64. Mousavi A, Vahdat S, Baheiraei N, Razavi M, Norahan MH, Baharvand H. Multifunctional conductive biomaterials as

promising platforms for cardiac tissue engineering. ACS Biomater Sci Eng. 2020;7(1):55-82.

- [65] 65. Zhang Y-Z, El-Demellawi JK, Jiang Q, Ge G, Liang H, Lee K, et al. MXene hydrogels: fundamentals and applications. Chem Soc Rev. 2020;49(20):7229-51.
- [66] 66. Yan J, Lu Y, Chen G, Yang M, Gu Z. Advances in liquid metals for biomedical applications. Chem Soc Rev. 2018;47(8):2518-33.
- [67] 67. Athukorala SS, Tran TS, Balu R, Truong VK, Chapman J, Dutta NK, et al. 3D Printable Electrically Conductive Hydrogel Scaffolds for Biomedical Applications: A Review. Polymers (Basel). 2021;13(3).
- [68] 68. Choe G, Oh S, Seok JM, Park SA, Lee JY. Graphene oxide/alginate composites as novel bioinks for three-dimensional mesenchymal stem cell printing and bone regeneration applications. Nanoscale. 2019;11(48):23275-85.
- [69] 69. Izadifar M, Chapman D, Babyn P, Chen X, Kelly ME. UV-assisted 3D bioprinting of nanoreinforced hybrid cardiac patch for myocardial tissue engineering. Tissue Engineering Part C: Methods. 2018;24(2):74-88.
- [70] 70. Malda J, Visser J, Melchels FP, Jüngst T, Hennink WE, Dhert WJA, et al. 25th Anniversary Article: Engineering Hydrogels for Biofabrication. Adv Mater. 2013;25(36):5011-28.
- [71] 71. Olate-Moya F, Arens L, Wilhelm M, Mateos-Timoneda MA, Engel E, Palza H. Chondroinductive alginate-based hydrogels having graphene oxide for 3D printed scaffold fabrication. ACS Appl Mater Interfaces. 2020;12(4):4343-57.
- [72] 72. Serafin A, Culebras M, Oliveira JM, Koffler J, Collins MN. 3D printable electroconductive gelatin-hyaluronic acid materials containing polypyrrole nanoparticles for electroactive tissue engineering. Advanced Composites and Hybrid Materials. 2023;6(3):109.
- [73] 73. Basara G, Saeidi-Javash M, Ren X, Bahcecioglu G, Wyatt BC, Anasori B, et al. Electrically conductive 3D printed Ti(3)C(2)T(x) MXene-PEG composite constructs for cardiac tissue engineering. Acta Biomater. 2022;139:179-89.
- [74] 74. Ul Haq A, Montaina L, Pescosolido F, Carotenuto F, Trovalusci F, De Matteis F, et al. Electrically conductive scaffolds mimicking the hierarchical structure of cardiac myofibers. Sci Rep. 2023;13(1):2863.

- [75] 75. Mei T, Cao H, Zhang L, Cao Y, Ma T, Sun Z, et al. 3D Printed Conductive Hydrogel Patch Incorporated with MSC@GO for Efficient Myocardial Infarction Repair. ACS Biomater Sci Eng. 2024;10(4):2451-62.
- [76] 76. Luque GC, Picchio ML, Daou B, Lasa-Fernandez H, Criado-Gonzalez M, Querejeta R, et al. Printable Poly(3,4ethylenedioxythiophene)-Based Conductive Patches for Cardiac Tissue Remodeling. ACS Appl Mater Interfaces. 2024;16(27):34467-79.
- [77] 77. Ajdary R, Ezazi NZ, Correia A, Kemell M, Huan S, Ruskoaho HJ, et al. Multifunctional 3D-printed patches for long-term drug release therapies after myocardial infarction. Adv Funct Mater. 2020;30(34):2003440.
- [78] 78. Serafin A, Murphy C, Rubio MC, Collins MN. Printable alginate/gelatin hydrogel reinforced with carbon nanofibers as electrically conductive scaffolds for tissue engineering. Mater Sci Eng, C. 2021;122:111927.
- [79] 79. Zhao Y-D, Lai J-H, Wang M. 4D Printing of Self-Folding Hydrogel Tubes for Potential Tissue Engineering Applications. Nano LIFE. 2021;11(04):2141001.
- [80] 80. Senatov FS, Niaza KV, Zadorozhnyy MY, Maksimkin A, Kaloshkin S, Estrin Y. Mechanical properties and shape memory effect of 3D-printed PLA-based porous scaffolds. J Mech Behav Biomed Mater. 2016;57:139-48.
- [81] 81. Peralta Ramos ML, González JA, Fabian L, Pérez CJ, Villanueva ME, Copello GJ. Sustainable and smart keratin hydrogel with pHsensitive swelling and enhanced mechanical properties. Mater Sci Eng, C. 2017;78:619-26.